

PLANILLA DE ESPESOR ZINC SILICATO



PASARELA Nº 5 PLANOS DE REFERENCIA:

RLP-K13-PL-M-087-13-0007-H1
RLP-K13-PL-M-087-13-0008-H1
RLP-K13-PL-Q-087-13-0007-H1
RLP-K13-PL-Q-087-13-0008-H1
RLP-K13-PL-Q-087-13-0009-H1
RLP-K13-PL-L-087-13-0001-H1
RLP-K13-PL-L-087-13-0005-H1

PASARELA Nº 13 PLANOS DE REFERENCIA:

RLP-TKCRUDO-PL-M-087-13-0017-H1
RLP-TKCRUDO-PL-M-087-13-0018-H1
RLP-TKCRUDO-PL-Q-087-13-0014-H1

PASARELA Nº 18 PLANOS DE REFERENCIA:

RLP-TKCRUDO-PL-M-087-13-0001-H1
RLP-TKCRUDO-PL-M-087-13-0002-H1
RLP-TKCRUDO-PL-M-087-13-0003-H1
RLP-TKCRUDO-PL-Q-087-13-0001-H1
RLP-TKCRUDO-PL-Q-087-13-0002-H1
RLP-TKCRUDO-PL-Q-087-13-0003-H1

PASARELA Nº 11 PLANOS DE REFERENCIA:

RLP-BFOIL-PL-M-087-13-0003-H1
RLP-BFOIL-PL-M-087-13-0004-H2
RLP-BFOIL-PL-Q-087-13-0001-H2

PASARELAS Nº 5 - Nº 13 - Nº 18 - Nº 11



B13 Resumen

| | # | x | σ | ↓ | ↑ |
|-------------------|-----|------|----------|----|-----|
| Espesor (microns) | 201 | 89,8 | 14,9 | 54 | 166 |

PLANILLA DE ESPESOR ZINC SILICATO



B13 Lecturas

| # | Espesor (microns) | Tiempo |
|----|----------------------|---------------------|
| 1 | 92 | 2017-03-16 09:03:16 |
| 2 | 100 | 09:03:17 |
| 3 | 62 | 09:03:19 |
| 4 | 86 | 09:03:20 |
| 5 | 90 | 09:03:21 |
| 6 | 92 | 09:03:22 |
| 7 | 98 | 09:03:22 |
| 8 | 102 | 09:03:23 |
| 9 | 86 | 09:03:24 |
| 10 | 92 | 09:03:25 |
| 11 | 90 | 09:03:26 |
| 12 | 88 | 09:03:27 |
| 13 | 100 | 09:03:28 |
| 14 | 90 | 09:03:29 |
| 15 | 62 | 09:03:32 |
| 16 | 158 | 09:03:33 |
| 17 | 82 | 09:03:34 |
| 18 | 78 | 09:03:35 |
| 19 | 84 | 09:03:36 |
| 20 | 94 | 09:03:37 |
| 21 | 90 | 09:03:37 |
| 22 | 82 | 09:03:38 |
| 23 | 82 | 09:03:39 |
| 24 | 122 | 09:03:40 |
| 25 | 76 | 09:03:41 |
| 26 | 104 | 09:03:42 |
| 27 | 94 | 09:03:43 |
| 28 | 98 | 09:03:44 |
| 29 | 88 | 09:03:45 |
| 30 | 94 | 09:03:46 |
| 31 | 96 | 09:03:48 |
| 32 | 94 | 09:03:49 |
| 33 | 84 | 09:03:50 |
| 34 | 96 | 09:03:51 |
| 35 | 90 | 09:03:52 |
| 36 | 94 | 09:03:53 |
| 37 | 92 | 09:03:54 |
| 38 | 90 | 09:03:54 |
| 39 | 84 | 09:03:55 |
| 40 | 86 | 09:03:56 |
| 41 | 76 | 09:03:57 |
| 42 | 104 | 09:03:58 |
| 43 | 84 | 09:03:59 |

PLANILLA DE ESPESOR ZINC SILICATO



B13 Lecturas

| # | Espesor (microns) | | Tiempo |
|----|----------------------|------------|----------|
| 44 | 98 | | 09:04:00 |
| 45 | 98 | | 09:04:01 |
| 46 | 122 | | 09:04:02 |
| 47 | 82 | | 09:04:02 |
| 48 | 94 | | 09:04:03 |
| 49 | 86 | | 09:04:04 |
| 50 | 98 | | 09:04:05 |
| 51 | 90 | | 09:04:06 |
| 52 | 84 | | 09:04:07 |
| 53 | 108 | | 09:04:08 |
| 54 | 98 | | 09:04:09 |
| 55 | 92 | | 09:04:10 |
| 56 | 88 | | 09:04:11 |
| 57 | 100 | | 09:04:13 |
| 58 | 98 | | 09:04:14 |
| 59 | 76 | | 09:04:15 |
| 60 | 86 | | 09:04:16 |
| 61 | 76 | | 09:04:17 |
| 62 | 86 | | 09:04:17 |
| 63 | 98 | 2017-03-29 | 10:27:38 |
| 64 | 82 | | 10:27:39 |
| 65 | 86 | | 10:27:40 |
| 66 | 88 | | 10:27:41 |
| 67 | 96 | | 10:27:42 |
| 68 | 94 | | 10:27:43 |
| 69 | 92 | | 10:27:47 |
| 70 | 82 | | 10:27:48 |
| 71 | 98 | | 10:27:52 |
| 72 | 96 | | 10:27:53 |
| 73 | 100 | | 10:27:54 |
| 74 | 100 | | 10:27:55 |
| 75 | 90 | | 10:27:56 |
| 76 | 94 | | 10:27:57 |
| 77 | 74 | | 10:27:58 |
| 78 | 76 | | 10:27:59 |
| 79 | 86 | | 10:28:00 |
| 80 | 62 | | 10:28:01 |
| 81 | 72 | | 10:28:02 |
| 82 | 68 | | 10:28:03 |
| 83 | 54 | | 10:28:04 |
| 84 | 70 | | 10:28:05 |
| 85 | 66 | | 10:28:06 |
| 86 | 96 | | 10:28:06 |

PLANILLA DE ESPESOR ZINC SILICATO



B13 Lecturas

| # | Espesor (microns) | Tiempo |
|-----|----------------------|----------|
| 87 | 100 | 10:28:07 |
| 88 | 88 | 10:28:08 |
| 89 | 108 | 10:28:09 |
| 90 | 100 | 10:28:10 |
| 91 | 98 | 10:28:11 |
| 92 | 82 | 10:28:12 |
| 93 | 102 | 10:28:13 |
| 94 | 102 | 10:28:14 |
| 95 | 98 | 10:28:15 |
| 96 | 96 | 10:28:16 |
| 97 | 90 | 10:28:17 |
| 98 | 92 | 10:28:17 |
| 99 | 98 | 10:28:18 |
| 100 | 98 | 10:28:27 |
| 101 | 102 | 10:28:28 |
| 102 | 166 | 10:28:29 |
| 103 | 86 | 10:28:30 |
| 104 | 80 | 10:28:30 |
| 105 | 80 | 10:28:32 |
| 106 | 92 | 10:28:32 |
| 107 | 96 | 10:28:33 |
| 108 | 80 | 10:28:34 |
| 109 | 84 | 10:28:35 |
| 110 | 82 | 10:28:36 |
| 111 | 78 | 10:28:37 |
| 112 | 86 | 10:28:37 |
| 113 | 88 | 10:28:38 |
| 114 | 88 | 10:28:39 |
| 115 | 88 | 10:28:40 |
| 116 | 122 | 10:28:41 |
| 117 | 78 | 10:28:42 |
| 118 | 78 | 10:28:43 |
| 119 | 74 | 10:28:44 |
| 120 | 58 | 10:28:44 |
| 121 | 68 | 10:28:45 |
| 122 | 76 | 10:28:46 |
| 123 | 86 | 10:28:47 |
| 124 | 96 | 10:28:48 |
| 125 | 88 | 10:28:49 |
| 126 | 88 | 10:28:50 |
| 127 | 74 | 10:29:19 |
| 128 | 86 | 10:29:19 |
| 129 | 80 | 10:29:20 |

PLANILLA DE ESPESOR ZINC SILICATO



B13 Lecturas

| # | Espesor (microns) | Tiempo |
|-----|----------------------|----------|
| 130 | 84 | 10:29:21 |
| 131 | 98 | 10:29:22 |
| 132 | 84 | 10:29:23 |
| 133 | 104 | 10:29:23 |
| 134 | 94 | 10:29:27 |
| 135 | 78 | 10:29:28 |
| 136 | 90 | 10:29:29 |
| 137 | 110 | 10:29:30 |
| 138 | 88 | 10:29:31 |
| 139 | 142 | 10:29:32 |
| 140 | 76 | 10:29:32 |
| 141 | 98 | 10:29:33 |
| 142 | 78 | 10:29:34 |
| 143 | 86 | 10:29:35 |
| 144 | 82 | 10:29:36 |
| 145 | 82 | 10:29:38 |
| 146 | 80 | 10:29:38 |
| 147 | 128 | 10:29:39 |
| 148 | 94 | 10:29:41 |
| 149 | 70 | 10:29:42 |
| 150 | 76 | 10:29:43 |
| 151 | 78 | 10:29:43 |
| 152 | 78 | 10:29:44 |
| 153 | 74 | 10:29:45 |
| 154 | 98 | 10:29:46 |
| 155 | 90 | 10:29:47 |
| 156 | 108 | 10:30:15 |
| 157 | 106 | 10:30:17 |
| 158 | 94 | 10:30:18 |
| 159 | 92 | 10:30:19 |
| 160 | 88 | 10:30:19 |
| 161 | 94 | 10:30:20 |
| 162 | 166 | 10:30:21 |
| 163 | 74 | 10:30:22 |
| 164 | 78 | 10:30:23 |
| 165 | 82 | 10:30:23 |
| 166 | 86 | 10:30:24 |
| 167 | 76 | 10:30:25 |
| 168 | 92 | 10:30:26 |
| 169 | 82 | 10:30:27 |
| 170 | 108 | 10:30:27 |
| 171 | 98 | 10:30:28 |
| 172 | 90 | 10:30:30 |


PLANILLA DE ESPESOR ZINC SILICATO



B13 Lecturas

| # | Espesor (microns) | Tiempo |
|-----|----------------------|----------|
| 173 | 78 | 10:30:31 |
| 174 | 84 | 10:30:31 |
| 175 | 94 | 10:30:35 |
| 176 | 84 | 10:30:36 |
| 177 | 80 | 10:30:37 |
| 178 | 98 | 10:30:38 |
| 179 | 92 | 10:30:38 |
| 180 | 104 | 10:30:39 |
| 181 | 80 | 10:30:40 |
| 182 | 94 | 10:30:41 |
| 183 | 82 | 10:30:42 |
| 184 | 86 | 10:30:42 |
| 185 | 80 | 10:30:43 |
| 186 | 80 | 10:30:44 |
| 187 | 88 | 10:30:45 |
| 188 | 90 | 10:30:46 |
| 189 | 86 | 10:30:47 |
| 190 | 92 | 10:30:48 |
| 191 | 88 | 10:30:49 |
| 192 | 86 | 10:30:50 |
| 193 | 70 | 10:30:50 |
| 194 | 90 | 10:30:51 |
| 195 | 90 | 10:30:52 |
| 196 | 86 | 10:30:53 |
| 197 | 100 | 10:30:54 |
| 198 | 84 | 10:30:55 |
| 199 | 92 | 10:30:56 |
| 200 | 80 | 10:30:57 |
| 201 | 78 | 10:30:58 |

PLANILLA DE ESPESOR ZINC SILICATO



PLANILLA DE ESPESOR EPOXI ALTOS SOLIDOS



PASARELA Nº 5 PLANOS DE REFERENCIA:

RLP-K13-PL-M-087-13-0007-H1
 RLP-K13-PL-M-087-13-0008-H1
 RLP-K13-PL-Q-087-13-0007-H1
 RLP-K13-PL-Q-087-13-0008-H1
 RLP-K13-PL-Q-087-13-0009-H1
 RLP-K13-PL-L-087-13-0001-H1
 RLP-K13-PL-L-087-13-0005-H1

PASARELA Nº 13 PLANOS DE REFERENCIA:

RLP-TKCRUDO-PL-M-087-13-0017-H1
 RLP-TKCRUDO-PL-M-087-13-0018-H1
 RLP-TKCRUDO-PL-Q-087-13-0014-H1

PASARELA Nº 18 PLANOS DE REFERENCIA:

RLP-TKCRUDO-PL-M-087-13-0001-H1
 RLP-TKCRUDO-PL-M-087-13-0002-H1
 RLP-TKCRUDO-PL-M-087-13-0003-H1
 RLP-TKCRUDO-PL-Q-087-13-0001-H1
 RLP-TKCRUDO-PL-Q-087-13-0002-H1
 RLP-TKCRUDO-PL-Q-087-13-0003-H1

PASARELA Nº 11 PLANOS DE REFERENCIA:

RLP-BFOIL-PL-M-087-13-0003-H1
 RLP-BFOIL-PL-M-087-13-0004-H2
 RLP-BFOIL-PL-Q-087-13-0001-H2

PASARELAS Nº 5 - Nº 13 - Nº 18 - Nº 11



B14 Resumen

| | # | x | σ | ↓ | ↑ |
|-------------------|-----|-------|----------|-----|-----|
| Espesor (microns) | 207 | 199,4 | 31,1 | 162 | 436 |

PLANILLA DE ESPESOR EPOXI ALTOS SOLIDOS



B14 Lecturas

| # | Espesor (microns) | Tiempo |
|----|-------------------|---------------------|
| 1 | 206 | 2017-03-18 09:06:53 |
| 2 | 184 | 09:06:54 |
| 3 | 190 | 09:06:55 |
| 4 | 198 | 09:06:56 |
| 5 | 298 | 09:06:57 |
| 6 | 190 | 09:06:57 |
| 7 | 264 | 09:06:58 |
| 8 | 282 | 09:06:59 |
| 9 | 206 | 09:07:00 |
| 10 | 170 | 09:07:01 |
| 11 | 296 | 09:07:02 |
| 12 | 200 | 09:07:03 |
| 13 | 208 | 09:07:03 |
| 14 | 190 | 09:07:04 |
| 15 | 208 | 09:07:05 |
| 16 | 182 | 09:07:06 |
| 17 | 202 | 09:07:06 |
| 18 | 192 | 09:07:07 |
| 19 | 282 | 09:07:08 |
| 20 | 196 | 09:07:09 |
| 21 | 310 | 09:07:10 |
| 22 | 208 | 09:07:10 |
| 23 | 196 | 09:07:11 |
| 24 | 168 | 09:07:12 |
| 25 | 268 | 09:07:13 |
| 26 | 200 | 09:07:14 |
| 27 | 188 | 09:07:14 |
| 28 | 206 | 09:07:15 |
| 29 | 192 | 09:07:17 |
| 30 | 186 | 09:07:17 |
| 31 | 286 | 09:07:18 |
| 32 | 192 | 09:07:23 |
| 33 | 192 | 09:07:24 |
| 34 | 206 | 09:07:24 |
| 35 | 232 | 09:07:25 |
| 36 | 196 | 09:07:26 |
| 37 | 194 | 09:07:27 |
| 38 | 186 | 09:07:27 |
| 39 | 186 | 09:07:28 |
| 40 | 296 | 09:07:29 |
| 41 | 208 | 09:07:30 |
| 42 | 206 | 09:07:31 |
| 43 | 190 | 09:07:32 |

PLANILLA DE ESPESOR EPOXI ALTOS SOLIDOS



B14 Lecturas

| # | Espesor (microns) | Tiempo |
|----|-------------------|---------------------|
| 44 | 168 | 09:07:33 |
| 45 | 166 | 09:07:34 |
| 46 | 162 | 09:07:34 |
| 47 | 172 | 09:07:35 |
| 48 | 196 | 09:07:36 |
| 49 | 206 | 09:07:37 |
| 50 | 210 | 09:07:38 |
| 51 | 194 | 09:07:38 |
| 52 | 188 | 09:07:39 |
| 53 | 174 | 09:07:40 |
| 54 | 196 | 09:07:41 |
| 55 | 190 | 09:07:41 |
| 56 | 176 | 09:07:43 |
| 57 | 196 | 09:07:44 |
| 58 | 204 | 09:07:45 |
| 59 | 186 | 09:07:45 |
| 60 | 184 | 09:07:46 |
| 61 | 176 | 09:07:47 |
| 62 | 186 | 09:07:48 |
| 63 | 180 | 09:07:49 |
| 64 | 182 | 09:07:49 |
| 65 | 184 | 09:07:50 |
| 66 | 192 | 09:07:51 |
| 67 | 196 | 09:07:52 |
| 68 | 198 | 2017-03-30 08:15:06 |
| 69 | 208 | 08:15:08 |
| 70 | 200 | 08:15:09 |
| 71 | 174 | 08:15:09 |
| 72 | 194 | 08:15:10 |
| 73 | 208 | 08:15:11 |
| 74 | 198 | 08:15:12 |
| 75 | 198 | 08:15:13 |
| 76 | 196 | 08:15:13 |
| 77 | 196 | 08:15:14 |
| 78 | 190 | 08:15:16 |
| 79 | 192 | 08:15:16 |
| 80 | 198 | 08:15:17 |
| 81 | 190 | 08:15:18 |
| 82 | 204 | 08:15:19 |
| 83 | 190 | 08:15:20 |
| 84 | 188 | 08:15:21 |
| 85 | 190 | 08:15:22 |
| 86 | 208 | 08:15:22 |

PLANILLA DE ESPESOR EPOXI ALTOS SOLIDOS



B14 Lecturas

| # | Espesor (microns) | Tiempo |
|-----|-------------------|----------|
| 87 | 204 | 08:15:23 |
| 88 | 214 | 08:15:25 |
| 89 | 202 | 08:15:25 |
| 90 | 182 | 08:15:26 |
| 91 | 192 | 08:15:27 |
| 92 | 212 | 08:15:28 |
| 93 | 196 | 08:15:29 |
| 94 | 198 | 08:15:30 |
| 95 | 204 | 08:15:31 |
| 96 | 200 | 08:15:31 |
| 97 | 196 | 08:15:32 |
| 98 | 188 | 08:15:33 |
| 99 | 208 | 08:15:34 |
| 100 | 186 | 08:15:35 |
| 101 | 198 | 08:15:36 |
| 102 | 192 | 08:15:37 |
| 103 | 200 | 08:15:37 |
| 104 | 172 | 08:15:38 |
| 105 | 196 | 08:15:39 |
| 106 | 200 | 08:15:40 |
| 107 | 200 | 08:15:41 |
| 108 | 206 | 08:15:42 |
| 109 | 194 | 08:15:43 |
| 110 | 200 | 08:15:43 |
| 111 | 190 | 08:15:44 |
| 112 | 192 | 08:15:46 |
| 113 | 188 | 08:15:47 |
| 114 | 200 | 08:16:46 |
| 115 | 200 | 08:16:47 |
| 116 | 202 | 08:16:48 |
| 117 | 190 | 08:16:49 |
| 118 | 180 | 08:16:50 |
| 119 | 172 | 08:16:50 |
| 120 | 178 | 08:16:51 |
| 121 | 168 | 08:16:52 |
| 122 | 170 | 08:16:53 |
| 123 | 172 | 08:16:57 |
| 124 | 182 | 08:17:11 |
| 125 | 214 | 08:17:12 |
| 126 | 178 | 08:17:12 |
| 127 | 166 | 08:17:13 |
| 128 | 376 | 08:17:14 |
| 129 | 194 | 08:21:22 |

PLANILLA DE ESPESOR EPOXI ALTOS SOLIDOS



B14 Lecturas

| # | Espesor (microns) | Tiempo |
|-----|-------------------|----------|
| 130 | 210 | 08:21:23 |
| 131 | 188 | 08:21:24 |
| 132 | 172 | 08:21:25 |
| 133 | 186 | 08:21:25 |
| 134 | 192 | 08:21:26 |
| 135 | 180 | 08:21:27 |
| 136 | 196 | 08:21:28 |
| 137 | 178 | 08:21:29 |
| 138 | 194 | 08:21:30 |
| 139 | 206 | 08:21:30 |
| 140 | 202 | 08:21:31 |
| 141 | 192 | 08:21:32 |
| 142 | 188 | 08:21:33 |
| 143 | 194 | 08:21:34 |
| 144 | 200 | 08:21:35 |
| 145 | 204 | 08:21:36 |
| 146 | 186 | 08:21:36 |
| 147 | 192 | 08:21:37 |
| 148 | 204 | 08:21:38 |
| 149 | 200 | 08:21:39 |
| 150 | 206 | 08:21:40 |
| 151 | 198 | 08:21:40 |
| 152 | 186 | 08:21:42 |
| 153 | 188 | 08:21:42 |
| 154 | 194 | 08:21:43 |
| 155 | 188 | 08:21:47 |
| 156 | 196 | 08:21:48 |
| 157 | 200 | 08:21:49 |
| 158 | 182 | 08:21:50 |
| 159 | 202 | 08:21:50 |
| 160 | 200 | 08:21:51 |
| 161 | 182 | 08:21:52 |
| 162 | 202 | 08:21:53 |
| 163 | 214 | 08:21:54 |
| 164 | 190 | 08:21:55 |
| 165 | 204 | 08:21:55 |
| 166 | 182 | 08:21:56 |
| 167 | 204 | 08:21:57 |
| 168 | 194 | 08:21:58 |
| 169 | 204 | 08:21:58 |
| 170 | 200 | 08:22:04 |
| 171 | 180 | 08:22:04 |
| 172 | 194 | 08:22:05 |

PLANILLA DE ESPESOR EPOXI ALTOS SOLIDOS




B14 Lecturas

| # | Espesor (microns) | Tiempo |
|-----|-------------------|----------|
| 173 | 194 | 08:22:06 |
| 174 | 186 | 08:22:07 |
| 175 | 190 | 08:22:08 |
| 176 | 186 | 08:22:09 |
| 177 | 204 | 08:22:10 |
| 178 | 186 | 08:22:11 |
| 179 | 206 | 08:22:12 |
| 180 | 188 | 08:22:13 |
| 181 | 182 | 08:22:13 |
| 182 | 192 | 08:22:14 |
| 183 | 174 | 08:22:15 |
| 184 | 192 | 08:22:16 |
| 185 | 194 | 08:22:17 |
| 186 | 198 | 08:22:17 |
| 187 | 196 | 08:22:18 |
| 188 | 192 | 08:22:19 |
| 189 | 190 | 08:22:20 |
| 190 | 192 | 08:22:21 |
| 191 | 200 | 08:22:21 |
| 192 | 292 | 08:22:22 |
| 193 | 198 | 08:22:23 |
| 194 | 436 | 08:22:24 |
| 195 | 198 | 08:22:25 |
| 196 | 194 | 08:22:25 |
| 197 | 200 | 08:22:28 |
| 198 | 194 | 08:22:29 |
| 199 | 182 | 08:22:30 |
| 200 | 198 | 08:22:31 |
| 201 | 192 | 08:22:31 |
| 202 | 188 | 08:22:32 |
| 203 | 166 | 08:22:33 |
| 204 | 192 | 08:22:34 |
| 205 | 184 | 08:22:34 |
| 206 | 202 | 08:22:35 |
| 207 | 188 | 08:22:36 |

PLANILLA DE ESPESOR EPOXI ALTOS SOLIDOS



B14



PLANILLA DE ESPESOR EPOXI ALTOS SOLIDOS



PASARELA Nº 5 PLANOS DE REFERENCIA:

RLP-K13-PL-M-087-13-0007-H1
RLP-K13-PL-M-087-13-0008-H1
RLP-K13-PL-Q-087-13-0007-H1
RLP-K13-PL-Q-087-13-0008-H1
RLP-K13-PL-Q-087-13-0009-H1
RLP-K13-PL-L-087-13-0001-H1
RLP-K13-PL-L-087-13-0005-H1

PASARELA Nº 13 PLANOS DE REFERENCIA:

RLP-TKCRUDO-PL-M-087-13-0017-H1
RLP-TKCRUDO-PL-M-087-13-0018-H1
RLP-TKCRUDO-PL-Q-087-13-0014-H1

PASARELA Nº 18 PLANOS DE REFERENCIA:

RLP-TKCRUDO-PL-M-087-13-0001-H1
RLP-TKCRUDO-PL-M-087-13-0002-H1
RLP-TKCRUDO-PL-M-087-13-0003-H1
RLP-TKCRUDO-PL-Q-087-13-0001-H1
RLP-TKCRUDO-PL-Q-087-13-0002-H1
RLP-TKCRUDO-PL-Q-087-13-0003-H1

PASARELA Nº 11 PLANOS DE REFERENCIA:

RLP-BFOIL-PL-M-087-13-0003-H1
RLP-BFOIL-PL-M-087-13-0004-H2
RLP-BFOIL-PL-Q-087-13-0001-H2

PASARELAS Nº 5 - Nº 13 - Nº 18 - Nº 11



B15 Resumen

| | # | x | σ | ↓ | ↑ |
|-------------------|-----|-------|----------|-----|-----|
| Espesor (microns) | 211 | 296,6 | 52,9 | 228 | 638 |

PLANILLA DE ESPESOR EPOXI ALTOS SOLIDOS



B15 Lecturas

| # | Espesor (microns) | Tiempo |
|----|-------------------|---------------------|
| 1 | 282 | 2017-03-21 11:42:05 |
| 2 | 282 | 11:42:06 |
| 3 | 298 | 11:42:07 |
| 4 | 280 | 11:42:11 |
| 5 | 290 | 11:42:12 |
| 6 | 292 | 11:42:13 |
| 7 | 284 | 11:42:13 |
| 8 | 300 | 11:42:15 |
| 9 | 288 | 11:42:16 |
| 10 | 268 | 11:42:16 |
| 11 | 286 | 11:42:17 |
| 12 | 288 | 11:42:18 |
| 13 | 286 | 11:42:19 |
| 14 | 292 | 11:42:20 |
| 15 | 272 | 11:42:21 |
| 16 | 292 | 11:42:22 |
| 17 | 272 | 11:42:23 |
| 18 | 292 | 11:42:24 |
| 19 | 284 | 11:42:24 |
| 20 | 270 | 11:42:25 |
| 21 | 278 | 11:42:26 |
| 22 | 278 | 11:42:27 |
| 23 | 288 | 11:42:28 |
| 24 | 270 | 11:42:29 |
| 25 | 290 | 11:42:30 |
| 26 | 284 | 11:42:31 |
| 27 | 272 | 11:42:31 |
| 28 | 290 | 11:42:32 |
| 29 | 288 | 11:42:33 |
| 30 | 282 | 11:42:34 |
| 31 | 290 | 11:42:35 |
| 32 | 280 | 11:42:35 |
| 33 | 290 | 11:42:36 |
| 34 | 298 | 11:42:39 |
| 35 | 286 | 11:42:40 |
| 36 | 280 | 11:42:41 |
| 37 | 302 | 11:42:42 |
| 38 | 266 | 11:42:43 |
| 39 | 272 | 11:42:43 |
| 40 | 284 | 11:42:44 |
| 41 | 298 | 11:42:45 |
| 42 | 276 | 11:42:46 |
| 43 | 286 | 11:42:47 |

PLANILLA DE ESPESOR EPOXI ALTOS SOLIDOS



B15 Lecturas

| # | Espesor (microns) | Tiempo |
|----|-------------------|---------------------|
| 44 | 292 | 11:42:48 |
| 45 | 294 | 11:42:49 |
| 46 | 286 | 11:42:52 |
| 47 | 286 | 11:42:53 |
| 48 | 406 | 11:42:55 |
| 49 | 294 | 11:42:57 |
| 50 | 242 | 11:42:59 |
| 51 | 274 | 11:43:01 |
| 52 | 310 | 11:43:03 |
| 53 | 258 | 11:43:05 |
| 54 | 256 | 11:43:06 |
| 55 | 238 | 11:43:08 |
| 56 | 228 | 11:43:10 |
| 57 | 268 | 11:43:11 |
| 58 | 296 | 11:43:12 |
| 59 | 286 | 11:43:13 |
| 60 | 282 | 11:43:14 |
| 61 | 306 | 11:43:14 |
| 62 | 278 | 11:43:15 |
| 63 | 290 | 11:43:16 |
| 64 | 304 | 11:43:17 |
| 65 | 276 | 11:43:18 |
| 66 | 284 | 11:43:19 |
| 67 | 280 | 11:43:20 |
| 68 | 264 | 11:43:20 |
| 69 | 284 | 11:43:21 |
| 70 | 296 | 11:43:22 |
| 71 | 298 | 11:43:24 |
| 72 | 292 | 11:43:25 |
| 73 | 316 | 11:43:28 |
| 74 | 296 | 11:43:34 |
| 75 | 296 | 11:43:36 |
| 76 | 334 | 11:43:39 |
| 77 | 406 | 11:43:42 |
| 78 | 446 | 11:43:44 |
| 79 | 566 | 11:43:52 |
| 80 | 264 | 2017-04-03 09:06:07 |
| 81 | 314 | 09:06:08 |
| 82 | 290 | 09:06:09 |
| 84 | 280 | 09:06:11 |
| 85 | 288 | 09:06:12 |
| 86 | 292 | 09:06:13 |
| 87 | 292 | 09:06:14 |

PLANILLA DE ESPESOR EPOXI ALTOS SOLIDOS



B15 Lecturas

| # | Espesor (microns) | Tiempo |
|-----|-------------------|----------|
| 88 | 282 | 09:06:15 |
| 89 | 284 | 09:06:16 |
| 90 | 284 | 09:06:17 |
| 91 | 278 | 09:06:18 |
| 92 | 270 | 09:06:19 |
| 93 | 292 | 09:06:19 |
| 94 | 302 | 09:06:20 |
| 95 | 264 | 09:06:22 |
| 96 | 286 | 09:06:23 |
| 97 | 278 | 09:06:23 |
| 98 | 268 | 09:06:24 |
| 99 | 276 | 09:06:26 |
| 100 | 294 | 09:06:26 |
| 101 | 270 | 09:06:27 |
| 102 | 270 | 09:06:28 |
| 103 | 282 | 09:06:29 |
| 104 | 296 | 09:06:30 |
| 105 | 300 | 09:06:36 |
| 106 | 296 | 09:06:36 |
| 107 | 294 | 09:06:37 |
| 108 | 278 | 09:06:38 |
| 109 | 300 | 09:06:39 |
| 110 | 296 | 09:06:40 |
| 111 | 276 | 09:06:41 |
| 112 | 280 | 09:06:42 |
| 113 | 276 | 09:06:43 |
| 114 | 278 | 09:06:44 |
| 115 | 308 | 09:06:46 |
| 116 | 288 | 09:06:46 |
| 117 | 298 | 09:06:47 |
| 118 | 288 | 09:06:48 |
| 119 | 292 | 09:06:49 |
| 120 | 302 | 09:06:50 |
| 121 | 284 | 09:06:51 |
| 122 | 302 | 09:06:52 |
| 123 | 284 | 09:06:56 |
| 124 | 272 | 09:07:00 |
| 125 | 264 | 09:07:01 |
| 126 | 280 | 09:07:02 |
| 127 | 288 | 09:07:03 |
| 128 | 272 | 09:07:04 |
| 129 | 262 | 09:07:05 |
| 130 | 284 | 09:07:06 |

PLANILLA DE ESPESOR EPOXI ALTOS SOLIDOS



B15 Lecturas

| # | Espesor (microns) | Tiempo |
|-----|-------------------|----------|
| 131 | 280 | 09:07:06 |
| 132 | 272 | 09:07:07 |
| 133 | 270 | 09:07:08 |
| 134 | 360 | 09:07:09 |
| 135 | 298 | 09:07:10 |
| 136 | 276 | 09:07:10 |
| 137 | 300 | 09:07:18 |
| 138 | 290 | 09:07:19 |
| 139 | 270 | 09:07:20 |
| 140 | 538 | 09:07:21 |
| 141 | 296 | 09:07:22 |
| 142 | 282 | 09:07:23 |
| 143 | 280 | 09:07:23 |
| 144 | 286 | 09:07:24 |
| 145 | 270 | 09:07:29 |
| 146 | 284 | 09:07:30 |
| 147 | 304 | 09:07:30 |
| 148 | 292 | 09:07:31 |
| 149 | 280 | 09:07:32 |
| 150 | 276 | 09:07:33 |
| 151 | 296 | 09:07:34 |
| 152 | 276 | 09:07:35 |
| 153 | 278 | 09:07:36 |
| 154 | 288 | 09:07:37 |
| 155 | 284 | 09:07:38 |
| 156 | 282 | 09:07:38 |
| 157 | 282 | 09:07:40 |
| 158 | 314 | 09:07:41 |
| 159 | 290 | 09:07:41 |
| 160 | 284 | 09:07:42 |
| 161 | 286 | 09:07:43 |
| 162 | 290 | 09:07:44 |
| 163 | 296 | 09:07:45 |
| 164 | 286 | 09:07:46 |
| 165 | 294 | 09:07:47 |
| 166 | 632 | 09:07:48 |
| 167 | 600 | 09:07:48 |
| 168 | 280 | 09:07:49 |
| 169 | 300 | 09:07:50 |
| 170 | 394 | 09:07:51 |
| 171 | 300 | 09:07:52 |
| 172 | 298 | 09:07:53 |
| 173 | 298 | 09:07:53 |

PLANILLA DE ESPESOR EPOXI ALTOS SOLIDOS



B15 Lecturas

| # | Espesor (microns) | Tiempo |
|-----|-------------------|----------|
| 174 | 290 | 09:07:54 |
| 175 | 288 | 09:07:55 |
| 176 | 290 | 09:08:14 |
| 177 | 284 | 09:08:15 |
| 178 | 298 | 09:08:16 |
| 179 | 302 | 09:08:41 |
| 180 | 308 | 09:08:42 |
| 181 | 302 | 09:08:43 |
| 182 | 280 | 09:08:44 |
| 183 | 286 | 09:08:45 |
| 184 | 296 | 09:08:45 |
| 185 | 278 | 09:08:46 |
| 186 | 292 | 09:08:47 |
| 187 | 284 | 09:08:48 |
| 188 | 278 | 09:08:49 |
| 189 | 302 | 09:08:50 |
| 190 | 286 | 09:08:51 |
| 191 | 272 | 09:08:52 |
| 192 | 296 | 09:08:53 |
| 193 | 280 | 09:08:53 |
| 194 | 284 | 09:08:55 |
| 195 | 276 | 09:08:56 |
| 196 | 386 | 09:08:56 |
| 197 | 278 | 09:08:57 |
| 198 | 274 | 09:08:58 |
| 199 | 286 | 09:08:59 |
| 200 | 288 | 09:09:00 |
| 201 | 638 | 09:09:01 |
| 202 | 278 | 09:09:01 |
| 203 | 284 | 09:09:02 |
| 204 | 288 | 09:09:03 |
| 205 | 284 | 09:09:04 |
| 206 | 288 | 09:09:05 |
| 207 | 288 | 09:09:06 |
| 208 | 294 | 09:09:07 |
| 209 | 396 | 09:09:08 |
| 211 | 300 | 09:09:09 |
| 212 | 290 | 09:09:10 |
| 213 | 288 | 09:09:11 |

PLANILLA DE ESPESOR EPOXI ALTOS SOLIDOS

